

**DUROPAL GmbH**  
Westring 19-21  
59759 Arnsberg  
Deutschland

Postfach 2760  
59753 Arnsberg

Telefon +49 (0) 29 32/3 02 - 0  
Fax +49 (0) 29 32/3 02 - 3 41  
info@duropal.com  
www.duropal.com

Sitz der Gesellschaft :  
Neumarkt  
Registergericht:  
Nürnberg, HRB 21658  
Geschäftsführer:  
Meinolf Hering  
Ulrike Hilger  
Markus Frevert

DUROPAL GmbH | Westring 19-21 | 59759 Arnsberg | Deutschland

Unser Zeichen    Ihr Ansprechpartner    Durchwahl    Fax    Email  
02932/302-    02932/302-

Datum  
17-06-2010

## Duropal declaration about ingredients in HPL, Compact HPL and HPL elements

We herewith declare that the paper used in production of Duropal HPL / Compact HPL is not bleached with any compounds that contain or give rise to elemental chlorine during the manufacturing process.

Hazard identification:

According to EN 438 a.m. products are classified as non-hazardous / non-dangerous goods.

Composition / information on ingredients:

<u>Name</u>	<u>%</u>
Paper	10-60
Phenol / formaldehyde resin	10-60
Melamine formaldehyde resin	10-30
Paper pigmented	<10
Plasticizers, unspecified	<10
Fire retardant, unspecified	<10

Above ingredients are bound together. Residual reactants may be released including.

The production of chipboards is externally audited with regard to PCP / Pentachlorophenol and Lindan, certification is available. Other fungicides or pesticides do not form part of the audit procedure or requirement.

Regarding the wood used in the production of chipboard, we are obliged to and meet the requirements set out according to the regulation of recycled wood and forbidden chemicals.

Blatt 2 zum Brief vom 17.06.2011

These German national standards are according to and fulfil the respective European standards.

Worktop boards / Quadra profile for customer Bench Top City PTY LTD

The board supplied to Australia is classified as

- o Hyfob / EPFS grade
- o "Hyfob" relates to moisture resistance
- o EPFS relates to formaldehyde emission classification

EPFS board EN 312, res. EN 120 perforator test method,  $\leq 4$  mg HCHO-Formaldehyde / 100 g bone dry board.

Our quality management system is certified acc. to DIN EN ISO 9001:2008 and DIN EN ISO14001:2009.



Thorsten Heilf  
Duropal quality management



Peter Röhr  
Duropal product- decor management